

THE EXTRA TEMPTATION



- ✓ soft surface
- ✓ ultra-matt surface
- ✓ good scratch resistance
- ✓ good tear resistance
- ✓ improved sweat resistance
- ✓ good fingerprint resistance
- ✓ better bonding
- ✓ no ghosting
- ✓ cond. hot foil stampable*
- ✓ overcoatable*
- ✓ glueable*

*see reverse page

SPECIFICATION

The TroTEMPTATION-X WET is an acrylic coated, biaxially oriented polypropylene foil; the thickness of the film is 17 µm (± 5 %); the foil can be used for materials of various kinds. This film is developed for print products, which are in daily use. Furthermore the film is excellent in recto – verso (both side lamination) applications. In contrast to other films with soft touch effects there is no blocking of the stack. No ghosting effects appear (for example spot coating, hot foil stamping). It is suitable for lamination with all commercial adhesives (water based, solvent free, solvent based).

PROPERTIES OF THE FILM:

1. soft surface
2. ultra-matt surface
3. modified scratch- and scrub resistance
4. good tear resistance
5. improved sweat resistance
6. good fingerprint resistance
7. modified backside (for better bonding at lamination process)
8. no ghosting
9. conditionally hot foil stampable (depending on subject and material, test required)
10. suitable for spot coatings with radical UV-curing systems (test required)
11. glueable (test required)

QUALITY

Each master roll is tested and logged for gloss, surface energy, bonding and coating homogeneity before, during and after the coating process.
The reels have maximum winding and cutting quality.
At the beginning of each production process (change of varnish or film batch), a few meters get laminated and will be reviewed by our quality department.
Slight differences in the color of ready-made rolls can occur throughout the production process, are normal and are only visible on the roll. They have no negative impact on the finished end product.

SIZE AND PACKAGING

The films are available in widths from 160 mm to 1,440 mm. Each roll is wound on a 3" (76.2 mm) core and has at least 3,000 running meters on it. For each splice, we deliver 50 extra service meters. The coating is on the outside of the roll.

TYPE	TroTEMPTATION-X WET
THICKNESS	17 µm ± 5 %
WEIGHT	≈ 13.6 g/m ²
YIELD	≈ 73.53 m ² /kg
FREE SURFACE ENERGY	≥ 40.0 mN/m *
GLOSS 85 °	11.5 ± 3 **

* Measured with KRÜSS Surface Analyzer

** Please notice that the gloss measurement of very matt surfaces is with the geometry of 85°.

If using the geometry of 60°, the gloss value will be under one and not in the metering range anymore.